



TECHNICAL SPECIFICATION SHEET

APEX KASCHIERLINER

CONSTRUCTION



PIW
PCW
Pigmentstrich

Grade Name : GD 2 APEX KASCHIERLINER

GEWICHT	DICKE	BERSTDRUCK	SCT quer
g/m ²	µm	kPa	kN/m
160	180	330	2.3
180	200	380	2.7
195	220	395	2.8
210	240	410	3.0
230	260	430	3.2
250	280	450	3.4

EIGENSCHAFTEN	WERT	TOLERANZEN	PRÜFNORM
Weißgrad Decke (% Elrepho)	83	- 1	ISO 2470-2
Glätte PPS Decke (µm)	1.5	≤ 1.8	ISO 8791-4
Glanz 75° (%)	> 50		ISO 8254
Gewicht (g/m ²)		+/- 2 %	EN ISO 536
Dicke (µm)		+/- 5 %	EN 20534
Berstdruck (kPa)		- 10 %	ISO 2759
SCT quer (kN/m)		- 0.3	ISO 9895
Prüfklima	23° C 50 %	+/- 1° C +/- 2 % rF	EN ISO 186